



Sales Office:  
 Engineered Synthetic Products, Inc.  
 Tel (770) 564-1857  
 Fax (770) 564-1818  
 www.espsynthetics.com

**Geotextile Product Description Sheet  
 SKAPS GE-114  
 Nonwoven Geotextile**

SKAPS GE-114 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GE-114 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. SKAPS GE-114 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight	ASTM D 5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	14.0 (475)
Grab Tensile	ASTM D 4632	lbs (kN)	390(1.73)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	135(0.60)
Thickness*	ASTM D 5199	mils (mm)	135(3.43)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	1045 (4.65)
Permittivity*	ASTM D 4491	sec <sup>-1</sup>	0.64
Permeability*	ASTM D 4491	cm/sec	0.25
Water Flow*	ASTM D 4491	gpm/ft <sup>2</sup> (l/min/m <sup>2</sup> )	50 (2037)
AOS	ASTM D 4751	US Sieve (mm)	100 (0.150)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	15 x 390
Square Yards Per Roll	650
Estimated Roll Weight – lbs	620

\* At the time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.

**SKAPS Industries,**  
 335 Athena Dr., Athens, GA 30601,  
 Phone:(706)-354-3700, Fax(706)-354-3737,  
 www.skaps.com

**Made in U.S.A.**