



## Geotextile Product Description Sheet

### SKAPS GT-150 Nonwoven Geotextile

SKAPS GT-150 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPSGT-150 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. SKAPS GT-150 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	5.25 (180)
Grab Tensile	ASTM D 4632	lbs (kN)	135 (0.60)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	55(0.24)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	350 (1.56)
Permittivity*	ASTM D 4491	sec <sup>-1</sup>	1.6
Water Flow*	ASTM D 4491	gpm/sq. ft.	115
AOS*	ASTM D 4751	US Sieve (mm)	70 (0.212)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	12.5 x 360 / 15 x 300
Square Yards Per Roll	500
Estimated Gross Roll Weight – lbs	187

\* At the time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.

**SKAPS Industries,**  
335 Athena Drive, Athens GA 30601  
Phone:(706)-354-3700, Fax(706)-354-3737,  
[www.skaps.com](http://www.skaps.com)

**Made in U.S.A.**